Synthesis of Nanocrystalline Iron(III) trifluoride from Molecular Precursors and its Liand Na-ion Storage Properties

<u>C. P. Guntlin^{1,2}</u>, T. Zünd^{1,2}, M. Wörle¹, K. V. Kravchyk^{1,2}, M. I. Bodnarchuk², M. V. Kovalenko^{1,2}*

¹Laboratory of Inorganic Chemistry, Department of Chemistry and Applied Bioscience, ETH Zürich, CH-8093 Zürich, Switzerland, ²Laboratory for Thin films and Photovoltaics, Empa – Swiss Federal Laboratories for Materials Science and Technology, CH-8600 Dübendorf, Switzerland

The performance demands placed on batteries for the use in electrical mobility and portable devices are enormous. Cathode materials remain a bottleneck for the further increase on energy density. A promising candidate compound featuring low cost and high natural abundance is iron trifluoride (FeF₃). It has been demonstrated that FeF₃ intercalates lithium with near theoretical capacity of 237 mAh/g [1], also with promising rate capability [2]. However, there remains a strong need to develop low-cost synthesis methods for this material in a nanoscale form, needed for maximizing the performance. Herein, we show a new synthesis for nanocrystalline FeF₃ based on a thermal decomposition of an organic precursor. Such inexpensive FeF₃ can be charged and discharged in a lithium half-cell at a reversible capacity of 155 mAh/g within 1 min (10 A/g) or even faster. After 100 cycles, a capacity retention of 88 % has been achieved. In a sodium-ion half-cell, a capacity of 160 mAh/g at a current rate of 0.2 A/g could be measured. [3]

Liu, J et al., J. Mater. Chem. A **2013**, 1, 1969
Ma, D. L. et al., Energy Environ Sci **2012**, 5, 8538
Guntlin, C. P., et al. J. Mater. Chem. A, **2017**, 5,7383